

Technical Data Sheet**IPETHENE® 830****Low Density Polyethylene****Description**

IPETHENE® 830 is a low density polyethylene injection molding grade. It exhibits high melt flow rate and high stiffness.

Applications

IPETHENE® 830 is used to produce lids, containers, toys, and domestic hollowware.

Quality, Environment and Safety Regulations

Material Safety Data Sheets and Product Safety declarations are available on our web site <http://www.caol.co.il>

Properties		Method	Typical Value*	Unit
Physical				
Melt Flow Rate	(190°C/2.16Kg)	ISO 1133	20	g/10min
Density		ISO 1183-A	0.920	g/cm ³
Mechanical				
Tensile Stress at Yield		ISO 527-2	11.5	MPa
Tensile Stress at Break		ISO 527-2	11.5	MPa
Tensile Strain at Break		ISO 527-2	80	%
Thermal				
Vicat Softening Temperature	(10N)	ISO 306	91	°C

**Typical values; not to be construed as specifications.*