

Technical Data Sheet
IPETHENE® 670
Low Density Polyethylene



Product Description

IPETHENE® 670 is a low-density polyethylene produced by high-pressure autoclave technology, designed for extrusion coating and lamination.

Features:	<ul style="list-style-type: none">• No additives• Low neck-in• Stable web properties• Good adhesion to substrates	<ul style="list-style-type: none">• Good moisture barrier• Low coating weight• Good organoleptic properties
------------------	--	---

Uses:	<ul style="list-style-type: none">• Coating paper, cardboard, aluminium foil, plastic film and fabric	<ul style="list-style-type: none">• Squeezable bottles• Master-batches
--------------	---	---

Processing Methods:	<ul style="list-style-type: none">• Blow molding• Compounding	<ul style="list-style-type: none">• Extrusion coating and lamination
----------------------------	--	--

Properties		Method	Typical Value*	Unit
Physical				
Melt Flow Rate	(190°C/2.16 kg)	ISO 1133	7.5	g/10 min
Density		ISO 1183-A	0.917	g/cm ³
Shore Hardness	'D' Scale	ISO 868	45	
Thermal				
Peak Melting Temperature	By DSC	ISO 11357-3	107	°C
Vicat Softening Temperature	(10 N)	ISO 306	90	°C

*Typical values; not to be construed as specifications.

Processing Recommendations

IPETHENE® 670 can be easily processed on conventional extrusion coating lines at melt temperature range 260-330°C.

Health, Quality, Regulations and Safety

This product is not classified as dangerous substance. Material safety data sheets, international standards certificates (e.g. ISO 9001) and other regulatory documents are available on our website. This product is not intended for use in medical or pharmaceutical applications and we do not support its use for such applications.

Carmel Olefins Ltd. POB 1468 Haifa 31014 Israel
Website: <http://www.Carmel-Olefins.co.il>
Email: techserv@caol.co.il

Date: June 2017

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Carmel Olefins extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors. Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products.