

Technical Data Sheet  
**CAPILENE® CE 50 E**  
 Specialty Polypropylene



### Product Description

**Developmental grade CAPILENE® CE 50 E** is a specialty soft polypropylene combining typical advantages of polypropylene random and heterophasic copolymers.

*The grade is being in development status, this is a preliminary data sheet and subjected to changes.*

|                            |  |  |
|----------------------------|--|--|
| <b>Features:</b>           | <ul style="list-style-type: none"> <li>• Very low flexural modulus</li> <li>• Excellent impact at sub-zero temperature</li> <li>• Very low stress whitening</li> </ul> | <ul style="list-style-type: none"> <li>• High gloss</li> <li>• Excellent transparency</li> <li>• Basic additive package</li> </ul> |
| <b>Uses:</b>               | <ul style="list-style-type: none"> <li>• Impact modifier for clear PP sheets</li> <li>• High clarity films</li> </ul>  | <ul style="list-style-type: none"> <li>• Corrugated sheets</li> <li>• Profiles</li> </ul>  |
| <b>Processing Methods:</b> | <ul style="list-style-type: none"> <li>• Injection molding</li> <li>• Compounding</li> </ul>   | <ul style="list-style-type: none"> <li>• Extrusion</li> <li>• Thermoforming</li> </ul>   |

| Properties                           |                   | Method     | Typical Value* | Unit              |
|--------------------------------------|-------------------|------------|----------------|-------------------|
| <b>Physical</b>                      |                   |            |                |                   |
| <b>Melt Flow Rate</b>                | (230°C/2.16 kg)   | ISO 1133   | 2              | g/10 min          |
| <b>Mechanical</b>                    |                   |            |                |                   |
| <b>Flexural Modulus</b>              | (5 mm/min)        | ISO 178    | 500            | MPa               |
| <b>Izod Impact Strength, notched</b> | (+23°C)           | ISO 180    | 45             | kJ/m <sup>2</sup> |
| <b>Izod Impact Strength, notched</b> | (-20°C)           | ISO 180    | 7.5            | kJ/m <sup>2</sup> |
| <b>Thermal</b>                       |                   |            |                |                   |
| <b>Vicat Softening Temperature</b>   | (10 N)            | ISO 306    | 126            | °C                |
| <b>Heat Deflection Temperature</b>   | (0.45 MPa)        | ISO 75-2   | 64             | °C                |
| <b>Optical</b>                       |                   |            |                |                   |
| <b>Haze</b>                          | (1 mm plaque)     | ASTM D1003 | 25             | %                 |
| <b>Haze**</b>                        | (50 µm film)      | ASTM D1003 | 0.8            | %                 |
| <b>Gloss**</b>                       | (45°, 50 µm film) | ASTM D2457 | 91             | %                 |

\*Typical values; not to be construed as specifications.

\*\* Measured on 50 µm cast film.

### Health, Quality, Regulations and Safety

This product is not classified as dangerous substance. Material safety data sheets, international standards certificates (e.g. ISO 9001) and other regulatory documents are available on our website. This product is not intended for use in medical or pharmaceutical applications and we do not support its use for such applications.

Carmel Olefins Ltd. POB 1468 Haifa 31014 Israel  
 Website: <http://www.Carmel-Olefins.co.il>  
 Email: [techserv@caol.co.il](mailto:techserv@caol.co.il)

**Date: December 2017**

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Carmel Olefins extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors. Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products.