

### Product Description

**CAPILENE® MU 32 EC** is a special polypropylene designed for high-speed extrusion coating and lamination.

- Features:**
- Good adhesion to substrates
  - High temperature resistance
  - Good organoleptic properties
  - Low neck-in
  - Low coating weight
  - Good moisture barrier

- Uses:**
- Coating paper, paperboard, woven or nonwoven fabrics, plastic films

- Processing Methods:**
- Extrusion coating
  - Lamination

Properties		Method	Typical Value*	Unit
<b>Physical</b>				
<b>Melt Flow Rate</b>	(230°C/2.16 kg)	ISO 1133	29	g/10 min
<b>Density</b>		ISO 1183	0.9	g/cm <sup>3</sup>
<b>Mechanical</b>				
<b>Flexural Modulus</b>	(5 mm/min)	ISO 178	1100	MPa
<b>Izod Impact Strength, notched</b>	(+23°C)	ISO 180	3	kJ/m <sup>2</sup>

\*Typical values; not to be construed as specifications.

### Typical Extrusion Coating Conditions

**CAPILENE® MU 32 EC** can be processed by commercial extrusion coating equipment within melt temperature range of 280-330°C.

### Health, Quality, Regulations and Safety

This product is not classified as dangerous substance. Material safety data sheets, international standards certificates (e.g. ISO 9001) and other regulatory documents are available on our website. This product is not intended for use in medical or pharmaceutical applications and we do not support its use for such applications.