

CAPILENE® SP 75 AV

Polypropylene Impact Copolymer



Product Description

CAPILENE® SP 75 AV is a high flow polypropylene heterophasic copolymer intended for injection molding.

Features:	<ul style="list-style-type: none"> Nucleated Mold release Short cycle time 	<ul style="list-style-type: none"> Extremely high melt flow Excellent stiffness/impact balance
Uses:	<ul style="list-style-type: none"> Thin wall injection moulding Household items Garden furniture 	<ul style="list-style-type: none"> Big and complex parts Containers Toys
Processing Methods:	<ul style="list-style-type: none"> Injection molding 	

Properties		Method	Typical Value*	Unit
Physical				
Melt Flow Rate	(230°C/2.16 kg)	ISO 1133	80	g/10 min
Mechanical				
Tensile Stress at Yield	(50 mm/min)	ISO 527-2	19	MPa
Tensile Strain at Yield	(50 mm/min)	ISO 527-2	6	%
Flexural Modulus	(5 mm/min)	ISO 178	950	MPa
Izod Impact Strength, notched	(+23°C)	ISO 180	10	kJ/m ²
Izod Impact Strength, notched	(-20°C)	ISO 180	7	kJ/m ²
Thermal				
Vicat Softening Temperature	(10 N)	ISO 306	145	°C
Heat Deflection Temperature	(0.45 MPa)	ISO 75-2	75	°C

*Typical values; not to be construed as specifications.

Health, Quality, Regulations and Safety

This product is not classified as dangerous substance. Material safety data sheets, international standards certificates (e.g. ISO 9001) and other regulatory documents are available on our website. This product is not intended for use in medical or pharmaceutical applications and we do not support its use for such applications.